## JP-S50-127930A

## 2. Claims:

A method of coating an inorganic paint, characterized in that the method comprises coating an inorganic paint which contains a silica sol or/(and) a silicate salt or/(and) a modified silicate salt, and phosphoric acid or/(and) a phosphate salt or/(and) a condensed phosphate salt, as a main component, and optionally contains a pigment, a filler, a subsidiary material and the like, and then dispersing a metal powder thereon, or in that the method comprises mixing the inorganic paint and a metal powder in advance, and then coating the mixture.